

EDM klodser i Hårdmetal

15M+ eller 11C+			K311+	
Tykkelse (mm)	Bredde (mm)	Længde (mm)	Tykkelse (mm)	Bredde/længde (mm)
1,55	76/101	101		
3,15	76/101	101		
4,75	76/101	101		
6,35	76/101	101	6,35	101/101
7,95	76/101	101	9,50	101/101
9,50	76/101	101	12,70	101/101
12,70	76/101	101	19,05	101/101
15,85	76/101	101	25,40	101/101
19,05	76/101	101	31,75	101/101
22,20	76/101	101		
25,40	76/101	101		
28,55	76/101	101		
31,75	76/101	101		

**K311+ med ekstra korrosionsbeskyttelse
ved tilsætning af TaNbC**

	Kvalitet: 15M+	Kvalitet: 11C+		Kvalitet: K311+
WC	86%	89%	WC	85%
Cobalt	14%	11%	Cobalt	11%
Grain size	submicron	Medium	TaNbC	3%
Density	14,12	14,4	Other	1%
TRS	450M psi	425M psi	Grain	Coarse
Rockwell A	90,1	89,7	Density	14
			Rockwell A	89,5